

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
24 February 2005 (24.02.2005)

PCT

(10) International Publication Number
WO 2005/016700 A3

(51) International Patent Classification⁷: B60R 13/02, B32B 5/22

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(21) International Application Number: PCT/US2004/026323

(22) International Filing Date: 11 August 2004 (11.08.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data: 60/495,931 14 August 2003 (14.08.2003) US

(71) Applicant (for all designated States except US): INTIER AUTOMOTIVE INC. [US/US]; 600 Wilshire Drive, Troy, MI 48084 (US).

(72) Inventor; and

(75) Inventor/Applicant (for US only): ASBURY, James, Daniel [US/US]; 30080 Cobblestone Court, New Hudson, MI 48165 (US).

(74) Agents: RASHID, Peter, J. et al.; Honigman Miller Schwartz and Cohn LLP, 32270 Telegraph Road, Suite 225, Bingham Farms, MI 48025 (US).


(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS.

[Continued on next page]

(54) Title: VEHICLE PANEL WITH REINFORCEMENT LAYER



WO 2005/016700 A3

(57) Abstract: A vehicle panel (10) includes a core layer (12) and a reinforcement layer (14) positioned on one or both sides of the core layer (12). The core layer (12) is made of a material with heat absorption or insulation properties, such as polypropylene, and the like. The reinforcement layer (14) is comprised of fiberglass strands (22) intermingled with a polymer (24) to form a blended composition having a linear density in a range between about 50 and 200g/m². The vehicle panel (10) may also include an adhesive layer (16) between a cover material (20) and the reinforcement layer (14) on one side of the core layer (12). The vehicle panel (10) may also include a scrim material (18) adjacent the reinforcement layer (14) on the opposite side of the core layer (12). The reinforcement layer (14) provides dimensional stability to the vehicle panel (10), while reducing the overall weight and thickness of the vehicle panel (10) as compared to conventional vehicle panels.